

Product Data Sheet

Product : Quadrant Polypenco Korea Nylatron® MC 701 - PA6, unfilled, cast

Categories : Polymer; Thermoplastic; Nylon ; Nylon 6; Nylon 6 , Cast

Material Notes : Data provided by Quadrant Polypenco Korea and Quadrant Engineering Plastic Products

Properties	Units	Test Methods	Nylatron® MC 701
Physical Properties			
Specific Gravity	g/cc	ASTM D 792	1.15
Water Absorption, Immersion, 24hr	%	ASTM D 570(2)	0.6
Water Absorption at Saturation, Immersion	%	ASTM D 570(2)	7.0
Mechanical Properties			
Rockwell Hardness, M	M scale	ASTM D 785	-
Rockwell Hardness, R	R scale	ASTM D 785	110
Hardness, Shore D	D	ASTM D 2240	-
Tensile Strength	MPa	ASTM D 638	66
Tensile Modulus	GPa	ASTM D 638	3.0
Elongation at Break	%	ASTM D 638	19
Flexural Yield Strength	MPa	ASTM D 790	100
Flexural Modulus	GPa	ASTM D 790	2.6
Compressive Strength	MPa	10% Def.; ASTM D 695	95
Compressive Modulus	GPa	ASTM D 695	2.70
Shear Strength	MPa	ASTM D 732	68
Coefficient of Friction; Dry vs. Steel	-	QTM 55007	-
K (wear) Factor	mm ³ /N-M	QTM 55010	-
Limiting Pressure Velocity; 4:1 safety factor	MPa-m/sec	QTM 55007	-
Izod Impact, Notched	J/m	ASTM D 256	26
Electrical Properties			
Surface Resistivity per Square	Ω	EOS/ESD S11.11	≥ 1X10 ¹³
Dielectric Constant	-	ASTM D 150	- @Frequency 1e+6 Hz
Dielectric Strength; Short term	kV/mm	ASTM D 149	15.7

Thermal Properties

Coefficient of Thermal Expansion; CTE, linear	µm/m-°C	ASTM E 831	95.0 @Temperature -40.0 - 149 °C
Thermal Conductivity	W/m-K	ASTM F 433	0.29
Melting point ; Crystalline, Peak	°C	ASTM D 3418	215
Maximum Service Temperature, Air	°C	Long Term	90
Deflection Temperature at 1.8 Mpa (264psi)	°C	ASTM D 648	-
Flammability, UL94 ; 1/8inch(Estimated Rating)	-	-	HB

Compliance Property

Comments

SVHC (Substance of Very High Concern)_REACH	Yes
---	-----

Descriptive Properties

Color	Grey
Machinability	1-10, 1=Easier to Machine

Chemical Resistance Properties

Acid, Strong (pH1-3)	Unacceptable
Acids, Weak	Limited
Alcohols	Limited
Alkalies, Weak	Unacceptable
Alkalies, Strong (pH 11-14)	Limited
Chlorinated Solvent	Limited
Conductive / Static Dissipative	No
Continuous Sunlight	Limited
Hot Water / Steam	Limited
Hydrocarbons – Aliphatic	Acceptable
Hydrocarbons – Aromatic	Acceptable
Inorganic Salt Solution	Acceptable
Ketones, Esters	Acceptable

Miscellaneous Properties

Targeted Usage	Load + Bearing
----------------	----------------

All information supplied by or on behalf of Polypenco Korea in relation to its products, in any form, is supported by research and believed to be reliable, but Polypenco Korea assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Polypenco Korea for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the

aforementioned information or products by the buyer.